



TEST REPORT

DATE: 01-16-2017

TEST NUMBER: 0233599

CLIENT	Davati Group-(MAXX Floors™)
---------------	-----------------------------

TEST METHOD CONDUCTED	ASTM F925 5 Minute Standard Test Method for Resistance to Chemicals of Resilient Flooring
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Planks-Loose Lay

TEST RESULTS

5 MINUTE RATINGS

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0
70% Isopropyl Alcohol	0	0	0
Mineral Oil	0	0	0
5% Sodium Hydroxide	0	0	0
5% Hydrochloric Acid	0	0	0
5% Ammonia	0	0	0
Bleach	0	0	0
5% Phenol	0	0	0
Gasoline	0	0	0
Sulfuric Acid	0	0	0
Kerosene	0	0	0
Olive Oil	0	0	0

RATING KEY
0 - No change (----)
1 - Slight change
2 - Moderate change
3 - Severe change

APPROVED BY: _____

Gary Asberry

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.